

PAPER BOX MASTER ROLLS AND LABELS

TAMPER EVIDENT



TAPES & LABELS



Description

Paper tamper evident laminate that “voids” when removed, **100% plastic free.**

Designed for use on cardboard boxes in the packaging industry and other similar surfaces.

Roll Data	Metric	Material Data	
Material Width	As shown on DR	Substrate	PAPER
Roll Length	As shown on DR	Thickness	55μ
Core I/D	76mm	Tensile strength (MD)	6.5
		Roughness PPS10 TS (μm)	1.5
		Transparency (%)	51
		Unger Oil Absorption (g/m2)	0.8

Adhesive Data

Adhesive	Formulated hot melt	Formulated hot melt
Adhesive thickness	30 to 40 gsm	
Softening point (Mettler drop point)	92°C	197.6°F
SAFT	59°C	138.9°F
Peel (20 min, glass)	35N / 25mm	309 inch pounds
Peel (24 hours, glass)	37N / 25mm	327 inch pounds
Tack (glass)	60N / 25mm	531
Shear (25mm x 25mm, 23°C, glass)	3 Days	3 Days (1" x1", 73.4°F, glass)
Shear (25mm x 25mm, 40°C, steel)	1.5 hours	1.5 hours (1" x1", 104°F, steel)

Note #1: Tests carried out using 50μ PET, 40gsm – tests cannot be carried out using tamper evident product as the tape is designed to “split” into 2 parts.

Note #2: The ingredients of the adhesive meet the compositional requirements of the American Food & Drug Administration regulations 21 CFR 175.105

Note #3: This product is not designed for food contact.

Note #4: Complies with ISO 17712, C-TPAT, OSHA and FDA standards, TSA -CCSP/CCSF, EU Counterfeit Medicines Directive Compliant



Packaging

Variants confirmed on artwork.

Storage

12 to 18 months

For the storage of the Tamper Evidence it is recommended that dry conditions between 10-20°C (50-68°F), kept in the box, out of direct sunlight.

The Shelf life, we recommend 12 months.

We control the whole manufacturing process as we manufacture from raw adhesive, inks and film. So we can tailor the tightness of the peel through to the colors, and levels of security we add to the tape from numbers through to security cuts to meet customer needs.

This data sheet does not constitute any warranty or specification whatsoever, either express or implied, on the part of Tamper Technologies Ltd; in particular tamper technologies ltd hereby excludes (1) any implied warranty regarding the accuracy, completeness or relevance of the data set out herein, some of which is based on external data which Tamper Technologies Ltd cannot control or verify, and (2) any implied warranty that the product herein described fits for a particular purpose; and (3) any implied warranty from any course of dealing, custom or usage. The final choice of the application of a product is therefore the sole responsibility of the end user.